

Material data sheet

voxeljet 3D printers

Plastic

Base material	PMMA particle material (55 µm)	PMMA particle material (85 µm)
Binder-type	Polypor B	Polypor C
Tensile strength	≥ 2.0 MPa	≥ 2.0 MPa
Yield point	1 %	1 %
Burn-out temperature	700 °C	600 °C
Residual ash content	< 0.01 weight %	< 0.01 weight %
Especially suited for	investment casting; design models	investment casting
Advantages	sharp edges; for highest accuracy and true-to-detail; reusable particle material	white colour; good for dyeing; burns out very well; reusable particle material

Technical data plastic parts

Layer thickness	150 µm
Resolution x, y	up to 600 dpi
Accuracy	± 0.4 % (min. ± 0.3 mm)

› Can be used for prototypes, illustrative models or lost models

› Precise layering & high accuracy

› Components of high complexity

› Economical production in batch sizes of one as well as in series production

› Infiltration in any colour

› Perfect for investment casting because of the base material PMMA

Suitable finishing treatment

	Wax	Epoxy
Tensile strength	see base material	up to 25 MPa
Softening temp.	73 °C	80 °C
Burn out temp.	see base material	-
Characteristics	smooth liquid, resistant surface	solid material, dyeable

Sand

Base material	raw silica sand, Cerabeads	silica sands of various grain sizes
Binder-type	Phenolic resin	Cold hardening furan resin
Bending strength	250 - 500 N/cm ²	≥ 220 N/cm ² (depending on the sand or binder)
Loss on ignition	adjustable (2.0 - 2.6 weight %)	approx. 2.5 weight %
Especially suited for	Sand casting of almost all alloys, especially steel or iron alloys.	Sand casting of almost all alloys.
Advantages	low gas shock, sand almost 100% recyclable, easy unpacking and highest edge sharpness.	Largest build volumes, fast build rates, most widely used.

› Any hybrid design and combination with conventional molds

› Complex cores manufactured and reproduced in one piece

› High flexibility with regard to quantity and mold design

› Close-to-production mold and casting properties

› Economical from prototype to small series production

Technical data sand parts

Layer thickness	200 - 300 µm; standard 300 µm
Resolution x, y	up to 300 dpi
Accuracy	± 0.1 % (min. ± 1.5 layer thickness)

Warranty/Disclaimer: The performance characteristics of these products may vary according to every individual case. voxeljet assumes no liability for the actual marketability of the products, as well as for the applicability of the products in individual cases. ©voxeljet. All rights reserved. The designations voxeljet, VX200, VX500, VX1000, VX2000 and VX4000 are registered trademarks of voxeljet AG. Specifications subject to change without notice. Validity: 01/2021. voxeljet is ISO 9001 - certified.