

# MATERIALS FOR 3D PRINTING **TITANIUM**



# Ti6Al4V (Grade 5)

# Titanium alloy

With high strength, low density, and resistance to corrosion, Ti6Al4V is the most widely used titanium alloy in the world.

We print titanium with Laser Powder Bed Fusion technology that prints in powder and uses a laser to weld the powder layers together. The technology requires support structure to attach the part to the build platform. The support is mechanically removed after printing.

The raw prints that come out of the printer have a surface finish similar to a cast metal part. The surface can subsequently be processed with various finishes.

The technology can print parts that meet ISO  $2768-m\ 1$  - however, the tolerances depend a lot on the geometry of the part.

MATERIAL PROPERTIES (STANDARD)	60 μm, 400 W – Raw print		
TENSILE STRENGTH [Rm]	1351 ±17 MPa		
YOUNG'S MODULUS [E]	113 ±7 GPa		
YIELD STRENGTH [Rp0,2]	1189 ± 49 MPa		
ELONGATION AT BREAK [A]	7 ±1 %		
REDUCTION OF CROSS SECTION [Z]	13 ±2 %		
VICKERS HARDNESS [HV10]	362 ± 11		
POWDER DENSITY	4,43 g/cm3		
PART DENSITY	>99,5 %		

SURFACE TEXTURE	Raw	Media blasted	Processed
Average roughness [Ra]	12 ±1	6 ±1	8,0

# Danish Technological Institute - Industrial 3D printing

Email: 3dprint@dti.dk Phone: 7220 1701 www.dti.dk/3dprinting



## Technology:

· Laser Powder Bed Fusion

#### **Printers:**

SLM Solutions - SLM500

#### **Build volume:**

• 500 x 280 x 360 mm

## Layer thickness

- 30 µm (fine)
- 60 µm (normal)

## Possible post-processing:

- De-stressing
- Heat treatment
- Deburring
- Media blasting
- Conventional processing

### Design features:

- · Minimum feature size 0,6 mm
- · Minimum channel size Ø2 mm
- · Minimum wall thickness 1 mm
- · Support for overhangs less than 45°
- Hole for emptying powder Ø5 mm

# Design guides:

- · Minimize the volume of the part as much as possible
- Avoid large changes in the cross-sectional area of the part
- Use camphors and roundings they are "free"
- Consider the print orientation in your design

